

POLIFLEX 180 ST

Characteristics	
Thermal class (temperature index)	H (180 °C)
Chemical composition	
Base resins	Polyesterimide
Overcoat	-
Bonding coat	-
Reference to the International Standards	IEC 60317-23 NEMA MW 77-C
UL – approval	File E 60641
Significant properties	<ul style="list-style-type: none">• Heat resisting winding wire which at increased temperature of the tinning bath can be tinned without previous removal of the enamel coating. Ø 0,050 mm at 450 ÷ 470 °C in 2" Ø 0,280 mm at 480 ÷ 500 °C in 2"