

ENAMELLED FLAT WIRE THERMOFLEX

Characteristics		
Conductor material	<ul style="list-style-type: none"> • Copper soft or with controlled proof stress (CPR) • Aluminium soft 	
Type of insulation	Modified polyvinyl formal (class 120)	
Insulation options	Enamel: grade 1 or 2	
Standards	IEC 60317-18	
Standard range of dimensions	Copper	Aluminium
cross-section (mm²)	3 to 85	10 to 85
width (mm)	2,00 to 18,00	4,00 to 15,00
thickness (mm)	1,00 to 6,00	1,40 to 6,00
ratio w/t	1,25 to 12,00	1,40 to 10,00
Applications	<ul style="list-style-type: none"> • Dry and Oil-filled transformers 	